

TINTED WOOD VARNISH

COSMOS LAC TINTED WOOD VARNISH ΧΡΩΜΑΤΙΣΤΟ ΒΕΡΝΙΚΙ YOAYE STRIKING EFFECT ON BAMBOO FURNITURE, ORNAMENTS, WOODEN DOORS AND SHUTTERS. ΕΝΤΥΠΩΣΙΑΚΗ ΕΦΑΡΜΟΓΗ ΣΕ ΕΠΙΠΛΑ ΜΠΑΜΠΟΥ, ΔΙΑΚΟΜΜΑΤΙΚΑ, ΨΥΛΙΝΕΣ ΠΟΡΤΕΣ, ΠΑΝΤΖΟΥΡΙΑ. 604

DESCRIPTION

Semi-transparent colored varnishes in aerosol form. Ideal for painting and protection of wooden surfaces. It can be used on painted or non-painted wooden furniture and any wooden objects.

PROPERTIES

- Viscosity: 18-25sec (Flow Cup DIN4, 20°C)
- Density: 0.8-1.1 g/L (Density Cup 100cm³/20°C, ASTM D 1475)
- VOC content: 779 g/L
- Flash Point: -104°C (based on propellant)
- Drying time

Touch (20°C, Humidity<65%): 5-10min Through dry (20°C, Humidity <65%): 1h Maximum hardness: 24h

- Coverage: 5m²/L
- Gloss: 80-90 GLOSS UNIT
 - (GLOSS METER 60°ASTM D 1471) Can Pressure: 4bar (20°C), 8 bar (50°C)
- Contents: 400ml

INSTRUCTIONS FOR USE

APPLICATION

Remove all dust and oil from the surface. Protect the area which you don't want to be painted. Shake the can thoroughly and spray at a distance of 25-30cm from the surface. Try the spray on testing surface. For better results apply 2-3 thin coats, 3-5 min apart.

Best application temperature: 10-25°C.

High moisture levels affect drying time and the final gloss.

AFTER USE

Spray holding the can inverted for 3". Clean the caps with solvent.

Store between 5-35°C. Do not store in vehicles.

CAP SYSTEM

SMART CAP

- Less overspray
- Extreme Coverage
- Fast drying
- Hard chisel lines
- Even coating
- Suitably for effects
- Dual way spraying

COLOR RANGE

601 MAHOGANY **607 TEAK**

603 WALNUT

604 OAK

SAFETY Request SDS

There are likely to be declinations in digital performance of shades. ISSUED DATE: 7/8/2024

VERSION: 01



COSMOS LAC A.E. PAINT INDUSTRY ©2024



MADE IN GREECE

